

SensiCare® PI

Polyisoprene Surgical Gloves




Made from Isolex, a proprietary synthetic polyisoprene, SensiCare surgical gloves are softer, more elastic, and more comfortable than latex alternatives to satisfy clinical needs and support safety initiatives.

Surgeons and staff can feel confident knowing that our surgical gloves are 100% inspected for pinholes, tears and visual defects. Medline's 0.65 AQL is 57% more stringent than the FDA requires. And our testing meets or exceeds ASTM, EN and ISO standards.

Specifications

Thickness:




Finish:



Grip:

Smooth finish with controlled grip for excellent handling.

Color:



Ordering information

Item No.	Size
71-ME9055	5.5
71-ME9060	6.0
71-ME9065	6.5
71-ME9070	7.0
71-ME9075	7.5
71-ME9080	8.0
71-ME9085	8.5
71-ME9090	9.0

50 pairs/box, 200 pairs/case

Features and benefits



Ideal for general surgery



Made from Medline's unique synthetic Isolex™ Polyisoprene formulation



Excellent choice as an overglove in combination with SensiCare PI Green




ARC (anti-roll down cuff) reduces cuff roll-down common with many gloves



Improved design to enhance comfort



This product is not made with natural rubber latex



Technical Sheet

SensiCare PI

Primary Material	Powder-Free Synthetic Isolex Polyisoprene with Synthetic Polymer Coating. ≤2.0 milligrams/glove of powder in accordance with ASTM D6124 and ISO 21171.
Donning Agent	Synthetic Polymer Coating (Inner surface coated for dry and damp hand donning)
Color	Cream (Provides contrast when using a dark-colored underglove)
Grip	Smooth (Specially treated surface for a balanced grip with blood and other fluids)
Former (Mold) Design	Anatomical to replicate hand shape and maximize comfort during long procedures
Cuff Design	Tapered, beaded cuff design to prevent rolldown. Reinforced material prevents tearing.
Chemical Additives (Accelerators)	Zinc Diethyldithiocarbamate (ZDEC) and Zinc Mercaptobenzothiazole (ZMBT)
Leachable Protein	No natural rubber latex proteins.
Thickness (per ASTM D3577 ≥ 0.10 mm)	Finger Tip 0.23 mm, Cuff 0.14 mm
Cuff Length (per EN455-2 ≥ 270 mm size 7.5)	300 mm
Force @ Break Before Accelerated Aging (per EN455-2 ≥ 9 N)	Meets/Exceeds
Force @ Break After Accelerated Aging (per EN455-2 ≥ 9 N, 7 days 70°C in an oven)	Meets/Exceeds
Elongation @ Break Before Accelerated Aging (per ASTM D3577 ≥ 650%)	Meets/Exceeds
Elongation @ Break After Accelerated Aging (per ASTM D3577 ≥ 450%, 7 days 70°C in an oven)	Meets/Exceeds
Freedom from Holes (per EN 455 AQL 1.5)	.65 AQL Final Inspection
Viral Penetration	Tested and passed, in accordance with ASTM F 1671
Chemotherapy	Please reach out to your Medline representative for USP-800 compliance and chemotherapy testing.
Chemical Resistance	The resistance to some chemicals has been assessed in accordance with EN 374-3. Results and recommendations for use with chemicals can be obtained on request.
Sterilization	Gamma Radiation, Sterility Assurance Level 10-6
Expiration Date	35 Months from Date of Manufacture. Manufacture and Expiration Dates are printed on packaging (YYYY-MM format).
Packaging	Polyethylene peel pouch material protects product during transport and storage from moisture and ozone and prevents tearing when opening to maintain a sterile environment. Packaged in space-saving folded configuration.
Storage Recommendations	Protect from freezing. Avoid excessive heat. Keep dry. Product should be shielded from direct sunlight, fluorescent lighting, X-rays, moisture and ozone. Do not store in temperatures above 40°C.
Country of Origin	Malaysia



For more information, visit bosma.org or call 800-362-5463.
Bosma Enterprises®, creating opportunities for individuals who are blind or visually impaired.
Your purchases provide employment for more than 100 people who are blind.

